

## MORTARS

Product	Al <sub>2</sub> O <sub>3</sub> %	SiO <sub>2</sub> %	Temperature Limit
QUICK BOND 3000	28.5	67.2	1650°C (3000°F)
BRIKSET	40.2	52.5	1650°C (3000°F)
BRIKSET THICK	40.2	52.5	1650°C (3000°F)
DURAL 65 MORTAR	65	27.7	1705°C (3100°F)
DURAL 81P MORTAR	76.7	10.6	1760°C (3200°F)
DURATAB MORTAR	88.8	3.3	1815°C (3300°F)
DURATAB C MORTAR	79.3	10.1	1815°C (3300°F)
DURATAB SC MORTAR	73.4	3.6	1705°C (3100°F)
BRIKSET 711	67.1	28	1705°C (3100°F)