

CASTABLES para FUNDICIÓN

SIN CEMENTO - DENSO

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
NANO-TEK® 418A	69.5	7.5	2.95 / 184	1705°C (3100°F)
NANO-TEK® 61HS	61.4	35.2	2.45 / 153	1705°C (3100°F)
FREE KAST 85	83.2	12.4	2.84 / 177	1760°C (3200°F)
QUICK-FIRE® 65	64.7	27.4	2.48 / 155	1650°C (3000°F)
QUICK-FIRE® 88	88.2	3.9	2.84 / 177	1650°C (3000°F)

ULTRA-BAJO CEMENTO - DENSO

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
V-CAST® 426A	80.4	10.4	3.14 / 196	1705°C (3100°F)
V-CAST® 701A	88.6	8.4	3.28 / 205	1705°C (3100°F)
V-CAST® 707A	80.9	9.8	3.17 / 198	1705°C (3100°F)
V-CAST® 712A	80.7	4.2	3.21 / 203	1650°C (3000°F)
V-CAST® 720A	74.4	5.6	3.04 / 190	1650°C (3000°F)
CW 921 CASTABLE	80.9	6.4	3.17 / 198	1650°C (3000°F)
CW 712 CASTABLE	80.6	3.6	3.21 / 203	1650°C (3000°F)
CW 920 CASTABLE	74.8	5.1	3.04 / 190	1650°C (3000°F)
CW 965 CASTABLE	69.0	28.0	2.65 / 165	1705°C (3100°F)
CASTMAX® MB HP	70.0	24.0	2.61-2.68 / 163-167	1790°C (3250°F)

BAJO CEMENTO - DENSO < 2.5% CaO

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
METAL KAST 90	93.9	4.3	3.01 / 190	1870°C (3400°F)
METAL KAST 85	82.6	12.4	2.85 / 178	1760°C (3200°F)
METAL KAST 85C	83.8	9.7	2.85 / 178	1705°C (3100°F)
METAL KAST 75	77.6	15.6	2.71 / 169	1760°C (3200°F)
METAL KAST 70	70.3	23.9	2.68 / 167	1760°C (3200°F)
METAL KAST 60	57.9	36.1	2.48 / 155	1705°C (3100°F)
CW 7929 CASTABLE	69.8	24.6	2.53 / 158	1705°C (3100°F)
TUFF-FLO 608	60.7	27.3	2.60 / 162	1650°C (3000°F)
QUICK CAST® 62	66.1	27.2	2.64 / 165	1705°C (3100°F)
DURACON® 28	45.3	48.7	2.31 / 144	1540°C (2800°F)
DURACON® 30	47.2	46.3	2.33 / 146	1650°C (3000°F)
DURACON® 32	63.1	31.6	2.54 / 158	1760°C (3200°F)



CEMENTO CONVENCIONAL - DENSO - > 2.5% CaO

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
HI AL KASTITE	96.2	0.2	2.74 / 171	1815°C (3300°F)
HI AL KASTITE X	96.5	0.1	3.12 / 195	1760°C (3200°F)
MINRO-AL® CAST A43	95.5	0	2.72 / 170	1815°C (3300°F)
KAST TECH 60	55.9	36.6	2.34 / 146	1650°C (3000°F)
LADLE KAST	55.9	37.8	2.24 / 140	1650°C (3000°F)
MINRO-FIRE CAST F80	53.2	39.3	2.24 / 140	1650°C (3000°F)
SUPER KASTITE 3000	59.1	34.8	2.29 / 143	1650°C (3000°F)
STEEL KAST	56.2	37.6	2.29 / 143	1650°C (3000°F)

BOMBEABLE / AUTO-FLUYENTE

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
V-CAST® 701A	88.6	8.4	3.28 / 205	1705°C (3100°F)
V-CAST® 707A	80.9	9.8	3.17 / 198	1705°C (3100°F)
V-CAST® 712A	80.7	4.2	3.21 / 203	1650°C (3000°F)
V-CAST® 720A	74.4	5.6	3.04 / 190	1650°C (3000°F)
TUFF-FLO 608	60.7	27.3	2.60 / 162	1650°C (3000°F)
TUFF-FLO 62 M	62.4	32.9	2.48 / 155	1760°C (3200°F)
TUFF-FLO 50	50.2	44.4	2.32 / 145	1650°C (3000°F)
TUFF-FLO FSM	34.8	61.3	2.20 / 137	1370°C (2500°F)
INSULMIX® 80LI P	42.4	46.8	1.28 / 80	1425°C (2600°F)
INSULMIX® 60LI P	39.7	47.7	1.02 / 64	1370°C (2500°F)

PROYECCIÓN (SHOTCRETING)

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
V-CAST® 426A	80.4	10.4	3.14 / 196	1705°C (3100°F)
V-CAST® 418A	70.9	7.5	2.95 / 184	1705°C (3100°F)
V-CAST® 397Cr	83.0	5.7	3.20 / 200	1760°C (3200°F)
NANO-TEK® 418A	69.5	7.5	2.95 / 184	1705°C (3100°F)
STACKCRETE® 60M	60.5	34.3	2.52 / 157	1705°C (3100°F)
STACKCRETE® 62M	61.7	32.8	2.45 / 153	1705°C (3100°F)
STACKCRETE® 608	59.3	28.3	2.60 / 162	1650°C (3000°F)
STACKCRETE® 85SiC				



MEZCLAS AISLANTES

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
BETAMAX® HS LT	50.6	29	1.37 / 85	1290°C (2350°F)
BETAMAX® 24 LT	42.4	39.7	1.23 / 77	1345°C (2450°F)
BETAMAX® 26 LT	52.9	36.4	1.27 / 79	1425°C (2600°F)
INSULMIX® 2025	15.4	38.3	0.32-0.48 / 20-30	1090°C (2000°F)
INSULMIX® 2460 LI	43.8	36	1.0 / 62	1315°C (2400°F)
INSULMIX® 25 HS	29.0	50.6	1.47 / 92	1371°C (2500°F)
INSULMIX® 2690 LI	42.5	46.3	1.44 / 90	1425°C (2600°F)

INSTALACIÓN MANUAL (HAND PACK)

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
KASTITE LHS	42.2	39.2	1.97 / 122	1425°C (2600°F)
GUNCAST® 26LI	45.9	41.1	2.07 / 129	1425°C (2600°F)
GUNCAST® 28LI	48.0	41.4	1.99 / 124	1540°C (2800°F)
QUICK-FIRE® PATCH B	78.5	10.0	2.53 / 158	1650°C (3000°F)
QUICK-FIRE® PATCH M	62.7	26.2	2.33 / 145	1650°C (3000°F)
PLASTER 55AC	51.6	37.3	2.21 / 138	1650°C (3000°F)

MORTEROS

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
QUICK BOND 3000	28.5	67.2	-	1650°C (3000°F)
BRIKSET	40.2	52.5	-	1650°C (3000°F)
BRIKSET THICK	40.2	52.5	-	1650°C (3000°F)
DURAL 65 MORTAR	65	27.7	-	1705°C (3100°F)
DURAL 81P MORTAR	76.7	10.6	-	1760°C (3200°F)
DURATAB MORTAR	88.8	3.3	-	1815°C (3300°F)
DURATAB C MORTAR	79.3	10.1	-	1815°C (3300°F)
DURATAB SC MORTAR	73.4	3.6	-	1705°C (3100°F)
BRIKSET 711	67.1	28	-	1705°C (3100°F)



EMPASTADO, ENLUCIDO (TROWELABLE)

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
T-COAT® 689M	3.5	8.5	2.05 / 128	1705°C (3100°F)
T-COAT® 692M	-	-	2.0 / 125	1650°C (3000°F)
CW KOTE 85	2.9	9.5	1.70 / 106	-
KASTITE LHS	42.2	39.2	1.97 / 122	1425°C (2600°F)
PLASTER 55AC	51.6	37.3	2.21 / 138	1650°C (3000°F)

CUBRIMIENTOS DELGADOS, TARRAJEO (WASHES)

Producto	Al ₂ O ₃ %	SiO ₂ %	Densidad (g/cm ³ / lb/ft ³)	Temperatura Límite
WASH 668A	79.6	9.9	1.92 / 120	1705°C (3100°F)
WASH 148A	91.7	5.8	-	1705°C (3100°F)
WASH 415CR	-	-	-	1815°C (3300°F)
CW 160G WASH	19.8	71.5	1.2 / 114	1650°C (3000°F)
ARMOR KOTE	40.1	43.4	1.52 / 95	1650°C (3000°F)
LADLE WELL SPRAY	11.8	80.6	1.75 / 109	1540°C (2800°F)

